

BLANK PAGE



Indian Standard REAFFIRMED

SPECIFICATION FOR PERFORATED STRIPS FOR TAKE-UP ROLLERS

First Reprint JANUARY 1977 (Incorporating Amendment No. 1)

UDC 67" /23 60' 14-418



© Copyright 1977

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002



Indian Standard SPECIFICATION FOR PERFORATED STRIPS FOR TAKE-UP ROLLERS

Cotton Weaving Machinery Components Sectional Committee, **TDC 29**

Chairman SHRI R. K. RAKSHIT

Representing Office of the Textile Commissioner, Bombay; and

Members

SHRI A. K. MALLIK (Alternate to

Shri R. K. Rakshit) SHRI T. R. ALURKAR

SHRI P. V. AMRUTE SHRI A. K. PHERWANI (Alternate)

SHRI B. N. BALIGA

SHRI S. M. NIMBKAR (Alternate)

SHRI RASIK R. BHATT

SHRI B. K. RAMACHANDER (Alternate)

SHRI M. LAKSHMINARAYAN SHRI CHAMPAKLAL P. MEHTA

SHRI BIPINCHANDRA M. JAGA-BHAIWALA (Alternate)

SHRI H. N. MISTRY

SHRI D. G. NAIK

SHRI K. C. PUROHIT SHRI B. M. SAPRE

Dr S. J. Shah

SHRI H. SKILLEN SHRI P. K. SRIRAMULU

SHRL D. B. AJGAONKAR (Alternate) SHRI AMRITLAL TONK

SHRI MAHAVIR PRASAD VAID

SHRI M. C. JHERWAR (Alternate)

SHRI BIMAL SWARUP VARMA

SHRI P. S. VENKATESALU

SHRI S. M. CHAKRABORTY, Director (Tex)

Ministry of Commerce

Engineering Association of India, Calcutta Ravi Industries Private Ltd, Bombay

Cooper Engineering Ltd, Satara Road

The Mysore Machinery Manufacturers Ltd.

Bangalore

The New Shorrock Spg & Mfg Co Ltd, Ahmedabad Gujarat Vepari Mahamandal, Ahmedabad

National Machinery Manufacturers Ltd, Thana (Maharashtra State)

Millowners' The Ahmedabad Association. Ahmedabad

The Bombay Textile Research Association, Bombay Central India Machinery Manufacturing Co Ltd,

The Textile & Allied Industries Research Organization, Baroda

The Upper India Chamber of Commerce, Kanpur Victoria Jubilee Technical Institute, Bombay

The Millowners' Association, Bombay

The Textile Association (India) Regd, Ahmedabad

Bengal Millowners' Association, Calcutta

The Southern India Millowners' Association. Coimbatore

Director General, ISI (Ex-officio Member)

Secretary SHRI D. R. KOHLI Assistant Director (Tex), ISI

(Continued on page 2)

INDIAN STANDARDS INSTITUTION MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG **NEW DELHI 110002**

(Continued from page 1)

Plain Calico Looms and Their Components Subcommittee, TDC 29: 1

Convener	Representing				
SHRI S. M. NIMBKAR	Cooper Engineering Ltd, Satara Road				
Members					
SHRI P. V. AMRUTE SHRI A. K. PHERWANI (Alternat	Ravi Industries Private Ltd, Bombay				
SHRI RASIK R. BHATT	The Mysore Machinery Manufacturers Ltd, Bangalore				
SHRI D. BHATTACHARYYA SHRI B. T. JAGASIA SHRI S. S. VAIDYA (Alternate)	The Textile Association (India) Regd, Ahmedabad The Khatau Makanji Spg & Wvg Co Ltd, Bombay				
SHRI S. S. MORAYE SHRI V. T. PARIKH	The Bombay Textile Research Association, Bombay Bharat Industries, Ahmedabad				
SHRI C. T. PARIKH (Alternate) SHRI R. K. RAKSHIT SHRI A. K. MALLIK (Alternate)	Office of the Textile Commissioner, Bombay				
SHRI B. M. SAPRE	Textile Machinery Manufacturers' Association, Bombay; and Central India Machinery Manu- facturing Co Ltd, Gwalior				
SHRI G. D. HALADI (Alternate)					
SHRI A. G. WAGLE SHRI P. K. SRIRAMULU SHRI D. G. AJGAONKAR (Altern	The Digvijay Spinning & Wvg Co Ltd, Bombay Victoria Jubilee Technical Institute, Bombay				

Indian Standard SPECIFICATION FOR PERFORATED STRIPS FOR TAKE-UP ROLLERS

O. FOREWORD

- 0.1 This Indian Standard was adopted by the Indian Standards Institution on 27 December 1967, after the draft finalized by the Cotton Weaving Machinery Components Sectional Committee had been approved by the Textile Division Council.
- **0.2** This standard is based on the manufacturing practices followed in the country in this field.
- 0.3 This standard contains clauses 3.3 and 6.3 which call for agreement between the buyer and the seller for permitting the buyer to use his option for selection to suit his requirements.
- **0.4** For assessing the roughness of fillet (see 2.3), the Bombay Textile Research Association, Bombay have taken up the work of evolving a suitable method. When the work is completed, the details of the method would be incorporated in this standard.
- 0.5 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test, shall be rounded off in accordance with IS: 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes requirements of perforated steel strips (fillets) used for covering take-up rollers of plain looms.

2. MANUFACTURE

- 2.1 Material Fillets shall be made from cold-rolled bright mild steel strips. The carbon content of the steel strip shall be 0.08 percent (Max).
- 2.2 Workmanship and Manufacture The strip should be punched to form holes all over the surface (see Fig. 1) in such a way that the edges of

^{*}Rules for rounding off numerical values (revised).

the holes protrude out of the surface of the strip making it rough. No hole shall cut the edge of strip on either side.

Note — If prescribed by the buyer, brass sheet may be used for the manufacture of fillets.




Fig. 1 Staggering of 7/8 Holes in a Fillet

- 2.3 Roughness of Fillet The surface of the fillet should be rough to such an extent that it does not allow the woven cloth to slip over it (that is, it grips the cloth) and at the same time does not damage the cloth in any way.
- 2.4 Finish The fillet shall be given an anti-rust finish.
- 3. REQUIREMENTS
- 3.1 Width The width of the fillet shall be 38 mm.
- 3.2 Thickness The thickness of the strip shall be 0.150 to 0.213 mm (or 38 to 35 SWG).
- 3.3 Pattern As agreed to between the buyer and the seller, the pattern of the fillet (staggering of holes) shall be 7/8, 9/10, 11/12, 16/17, 19/20 or 21/22. The staggering of holes in the fillet shall be as shown in Fig. 1.

NOTE 1 -- 7/8 holes means that there are 7 holes in a line across the width of the fillet and in the adjacent line there are 8 holes staggered as shown in Fig. 1.

NOTE 2 — The number of holes across the width of the fillet depends upon the quality of the cloth to be woven. The number of holes and quality of cotton cloth is given below

for the information and guidance of the buyer and the seller:

Pattern	Quality of Cloth		
7 /8	Coarse		
9/10, 11/12	Medium		
16/17	Fine		
19/20, 21/22	Superfine		

Note 3 — Diameter of holes and number of rows of holes per 5 cm along the length of the fillet in respect of various patterns should generally be as follows:

Pattern	Diameter of Hole, mm	Number of Rows 5 cm Along Length of Fillet		
7/8	1.2	12		
8/9	1.2	16		
9/10	0.8	16		
11/12	0-8	22		
16/17	0.4	26		
19/20	0.4	26		
21/22	0.4	32		

4. MARKING

- 4.1 Each roll of fillet (see 5.1) shall be marked at an appropriate place with the following:
 - a) Pattern (see 3.3); and
 - b) Manufacturer's name, initials or trade-mark.
 - 4.1.1 Fillet may also be marked with the ISI Certification Mark.

Note — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

5. PACKING

5.1 A length of 150 m of fillet shall be wrapped in the form of a roll. The roll shall then be oiled and wrapped with an inner layer of waterproof packing paper and finally with an outer layer of hessian.

- 5.1.1 The package shall bear the following information:
 - a) Length of the fillet;
 - b) Pattern; and
 - c) Name, initials or trade-mark of the manufacturer.

6. SAMPLING

- **6.1 Lot** All the rolls of fillets of the same pattern and manufactured from the same kind of material delivered to a buyer against one despatch note shall constitute a lot.
- 6.2 The conformity of the lot to the requirements of this standard shall be determined on the basis of the tests carried out on the sample drawn from it.
- 6.3 Unless otherwise agreed to between the buyer and the seller, the number of rolls to be selected at random shall be according to col 1 and 2 of Table 1.

TABLE 1 SAMPLE SIZE AND PERMISSIBLE NUMBER OF NON-CONFORMING ROLLS

(Clauses 6.3, 6.4 and 6.5)

Number of Rolls in the Lot	Number of Rolis to be Selected	Permissible Number of Non-conforming Rolls
(1)	(2)	(3)
Up to 25	5	0
26 ,, 100	8	0
101 ,, 300	13	0
301 " 500	20	1
501 ,, 1 000	32	1
1 001 and above	50	2

- 6.4 The rolls selected according to 6.3 shall be tested for width, thickness and pattern.
- 6.5 Criteria for Conformity The lot shall be declared as conforming to the requirements of this standard, if the number of rolls found defective in respect of any one or more of the characteristics tested in 6.4 does not exceed the corresponding number given in col 3 of Table 1.

PUBLICATIONS OF INDIAN STANDARDS INSTITUTION

INDIAN STANDARDS

Over 8 500 Indian Standards covering various subjects have been issued so far. Of these, the standards belonging to the Textile Group fall under the following categories:

Aeronautical textiles Chemical test methods Colour fastness of textile materials Cotton fabrics - handloom, khadi, and mill-made Dyestuffs Grading of fibres and yarns Grading of raw silk Hosiery Jute — bags and fabrics Jute mill accessories Narrow fabrics National flag of India Nylon fabrics Packaging codes Physical test methods Rayon fabrics

Rayon fabrics, handloom Ropes and cordages Sampling of textiles, methods for Silk fabrics - handloom and khadi Sizing and finishing materials Spinning machinery components Terminology Textile floor coverings Textile materials for fishing Textile mill accessories (other than jute mills) Twines Weaving machinery components Wool fabrics - handloom, khadi, and mill-made Yarn and similar structures Unclassified

OTHER PUBLICATIONS

ISI Bulletin (Published Eve	ry Moi	nth)					
Single Copy	•••	•••	•••	•••	•••	R _s	4.00
Annual Subscription	•••	•••	•••	•••	•••	Rs	36.00
Standards: Monthly Addition)TIS					_	
Single Copy	•••	•••	•••	•••	•••	Re	0.30
Annual Subscription	•••	•••	•••	•••	•••	Rs	3.00
Annual Reports (from 1948	-4 9 On	wards)	•••	•••	•••		to 6.00
ISI Handbook, 1975	•••	•••	•••	•••		Ŕs	30.00

INDIAN STANDARDS INSTITUTION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002

Telephone: 27 01 31 (20 lines)	Telegrams: Manaksanstha				
Regional Offices:		Telephone			
Western: Novelty Chambers, Grant Road Eastern: 5 Chowringhee Approach Southern: C.I.T. Campus, Adyar	BOMBAY 400007 CALCUTTA 700072 MADRAS 600020	37 97 29 23-08 02 41 24 42			
Branch Offices:					
'Pushpak', Nurmohamed Shaikh Marg, Khanpur 'F' Block, Unity Bldg, Narasimharaja Square Ahimsa Bldg, SCO 82-83, Sector 17C	AHMADABAD 380001 BANGALORE 560002 CHANDIGARH 160017	2 03 91 2 76 49 2 83 20			
5-8-56/57 L. N. Gupta Marg 117/418 B Sarvodaya Nagar B.C.I. Bldg (3rd Floor), Gandhi Maidan East	HYDERABAD 500001 KANPUR 208005 PATNA 800004	4 57 11 82 72 5 36 55			
Hantex Bldg (2nd Floor), Rly Station Road	TRIVANDRUM 695001	32 27			